

Elastohorse Rubber Technology Co.,  
#102, Green Field, Pakhowal Road,  
Ludhiana ,(Punjab) India.

**TECHNICAL DATA SHEET**  
*EPDM RECLAIM RUBBER / GRADE : ERT - EPDM*

**CHEMICAL PROPERTIES**

| <b>TECHNICAL DATA SPECIFICATION</b> | <b>EPDM RECLAIM RUBBER</b> |
|-------------------------------------|----------------------------|
| ACETONE EXTRACT (%)                 | 30 ± 5                     |
| ASH CONTENT (%)                     | 14 ± 2                     |
| CARBON BLACK (%)                    | 25 ± 2                     |
| VOLATILE MATTER (%)                 | 1.0 (Max)                  |
| RHC (%)                             | 30 (Min)                   |

**PHYSICAL PROPERTIES**

|                          |             |
|--------------------------|-------------|
| SPECIFIC GRAVITY (gm/cc) | 1.14 ± 0.02 |
| TENSILE STRENGTH (MPA)   | 60 Min.     |
| ELONGATTION (%)          | 375 Min.    |
| HARDNESS (Shore A)       | 55 ± 5      |
| MOONEY                   | 40 - 60     |
| VISCOSITY (1+ 4@100°C)   |             |