

Elastohorse Rubber Technology Co.,
#102, Green Field, Pakhowal Road,
Ludhiana ,(Punjab) India.

TECHNICAL DATA SHEET
HIGH TENSILE RECLAIM / GRADE : ERT - HT

CHEMICAL PROPERTIES

TECHNICAL DATA SPECIFICATION	HIGH TENSILE RECAIM
ACETONE EXTRACT (%)	14.6 ± 2
ASH CONTENT (%)	7 ± 2
CARBON BLACK (%)	28 ± 3
VOLATILE MATTER (%)	1.0 (Max)
RHC (%)	48 (Min)

PHYSICAL PROPERTIES

SPECIFIC GRAVITY (gm/cc)	1.13 ± 0.02
TENSILE STRENGTH (MPA)	90 Min.
ELONGATTION (%)	270 Min.
HARDNESS (Shore A)	59 ± 3
MOONEY	35 - 60
VISCOSITY (1+ 4@100°C)	