

Elastohorse Rubber Technology Co.,
#102, Green Field, Pakhowal Road,
Ludhiana ,(Punjab) India.

TECHNICAL DATA SHEET
NATURAL TUBE RECLAIM / GRADE : ERT - NT

CHEMICAL PROPERTIES

TECHNICAL DATA SPECIFICATION	NATURAL TUBE RECAIM
ACETONE EXTRACT (%)	11 ± 4
ASH CONTENT (%)	28 (Max)
CARBON BLACK (%)	20 ± 7
VOLATILE MATTER (%)	1.0 (Max)
RHC (%)	42 (Min)

PHYSICAL PROPERTIES

SPECIFIC GRAVITY (gm/cc)	1.25 ± 0.05
TENSILE STRENGTH (MPA)	40 Min.
ELONGATTION (%)	220 Min.
HARDNESS (Shore A)	55 ± 5
MOONEY	35 ± 10
VISCOSITY (1+ 4@100°C)	